



CONVERSION TABLE FOR YARNS

Denier	Decitex	ENGLISH NUMBERS		ENGLISH NUMBERS		LENGTH	
		Cotton	Flax	Worsted	Woollen	Meter/kg	Yards/lbs
100	111	11,11	53,15	148,5	79,74	90.000	44.644
150	167	35,43	99	53,16	116	60.000	29.763
210	233	25,33	70,79	38,01	83,14	42.800	21.280
300	333	17,72	49,5	26,58	58,14	30.000	14.881
360	400	14,76	41,25	22,15	48,45	25.000	12.401
400	444	13,29	37,13	19,94	43,61	22.500	11.161
420	467	12,64	35,31	18,96	41,47	21.400	10.615
500	556	10,63	29,70	15,95	34,88	18.000	8.929
540	600	9,86	27,60	14,8	32,36	16.700	8.284
600	667	8,86	24,75	13,29	29,07	15.000	7.441
630	700	8,44	23,60	12,70	27,71	14.300	7.093
720	800	7,38	20,63	11,08	24,23	12.500	6.201
800	889	6,67	18,65	10,01	21,90	11.300	5.581
840	933	6,32	17,66	9,48	20,74	10.700	5.313
900	1.000	5,91	16,50	8,86	19,38	10.000	4.960
1.000	1.111	5,31	14,85	7,97	17,44	9.000	4.484
1.100	1.222	4,83	13,50	7,35	15,85	8.180	4.058
1.200	1.333	4,43	12,38	6,80	14,54	7.500	3.720
1.500	1.667	3,54	9,9	5,32	11,63	6.000	2.976
1.650	1.833	3,22	8,99	4,83	10,56	5.450	2.703
2.000	2.222	2,66	7,43	3,99	8,72	4.800	2.232
2.200	2.444	2,42	6,75	3,62	7,93	4.090	2.029
2.500	2.778	2,13	5,94	3,19	6,98	3.600	1.786
3.000	3.333	1,77	4,95	2,68	5,81	3.000	1.488